

GRAND PACIFIC PETROCHEMICAL CORP

10TH FL, 1 NANJING E RD, SEC 4, TAIPEI 105 TW

D-100N**Acrylonitrile Butadiene Styrene (ABS), furnished as pellets**

| Color | Min Thk | Flame | | | | RTI | RTI | RTI |
|-------|---------|-------|-----|-----|--|------|-----|-----|
| | (mm) | Class | HWI | HAI | | Elec | Imp | Str |
| ALL | 1.5 | HB | - | - | | 60 | 60 | 60 |
| | 3.0 | HB | - | - | | 60 | 60 | 60 |

Comparative Tracking Index (CTI): **0**

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): -

Volume Resistivity (10^x ohm-cm) : -High-Voltage Arc Tracking Rate (HVTR): **2**High Volt, Low Current Arc Resis (D495): **6**

Dimensional Stability (%): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2012-08-31

Last Revised: 2012-09-13

© 2012 UL LLC

